

TECHNICAL SHEET
Art. SELIN

GENERAL DETAILS

NAME OF YARN:	SELIN
METRIC COUNT:	14.000
TEXTILE COUNT:	72 Tex x 1
NUMBER OF PLY:	4
COMPOSITION:	30% Silk - 70% Linen
PUNCHED DATA CODES:	30% SE - 70% LI
TYPE OF YARN:	Linear classic
SPINNING SYSTEM:	Woollen
MAUFACTURING:	Intime blend
CONVENTIONAL RATE APPLIED:	11,70%
AVERAGE REGAIN RATE APPLIED:	3,6% $\frac{#}{#}$ 3,8%

MATERIAL SPECIFICATIONS

TYPE OF FIBRE (1st component):	Silk
---------------------------------------	------

ANIMAL FROM WHICH IT IS HARVESTED:	Silkworm
SCIENTIFIC CLASSIFICATION:	<p>CLASS: <i>Insecta</i></p> <p>ORDER: <i>Lepidoptera</i></p> <p>FAMILY: <i>Bombycidae</i></p> <p>GENUS: <i>Bombyx</i></p> <p>SPECIES: <i>B. mori</i></p>
ORIGIN OF THE FIBRE:	Jiangsu and Zhejiang province (People's Republic of China)
LENGHT OF THE FIBRE:	Filament
QUALITY DEGREE	5A

TYPE OF FIBRE (2nd component):	Linen
PLANT FROM WHICH IT IS HARVESTED:	Linum usitatissimum
SCIENTIFIC CLASSIFICATION:	<p>CLASS: <i>Magnoliopsida</i></p> <p>ORDER: <i>Malpighiales</i></p> <p>FAMILY: <i>Linaceae</i></p> <p>GENUS: <i>Linum</i></p> <p>SPECIES: <i>Linum usitatissimum</i></p>
ORIGIN OF THE FIBRE:	Europe

TYPE:	Long Fibre
LENGHT OF THE FIBRE:	45 $\frac{3}{4}$ 55 mm
LENGHT OF THE FIBRE:	23 micron

TYPE OF DYE

SOLID COLOURS:	Dyed on tops
-----------------------	--------------

RECCOMENDED MACHINES

FLAT KNITTING MACHINE:	1 ply 12
CUT COTTON MACHINE:	1 ply 21 Gauges

ADVICE FOR WORKING

When removing stains from yarns with a high percentage of linen, it is very important that the processing is performed in premises with controlled temperature and moisture. When the temperature and moisture in the working premises are not controlled, a high number of breaks may take place, to the point of jeopardising the success of the stain removal. In such cases we recommend the installation of an industrial humidifier which can correct the moisture content. Alternatively, the yarn can be stored for at least 48 hours in a closed room with a domestic humidifier in operation, being withdrawn only at the moment of processing.

Furthermore, we suggest you the following: :

- Re-paraffin the yarn at low speed immediately before putting it in the machine.
- Avoid particularly difficult stitches, and experiment the product thoroughly before utilising it for large quantities.
- NEVER use re-paraffined or re-reeled reels of yarn together with original reels.
- Check the cloth constantly during processing and in the case of evident defects suspend work and phone us to report the problem

COMMERCIAL INFORMATION FOR ARTICLE SELIN

COLOURS:	18 SOLID COLOURS
SHADE CARD REFERENCE:	"SILK LINEN"
PRODUCTION MINIMUMS:	3,5 Kg. for solid colours
EXTRA CHARGES	To view the extra charges for twisting, dyeing and shipment which we apply for small productions, refer to the commercial information menu.
STANDARD PACK:	Cone of approx. 1 kg., each wrapped in a film of matt polythene to protect it from the light.
SPECIAL PACKAGES ON REQUEST:	<ul style="list-style-type: none">- Industrial or pre-treated yarn for knitting packed in skeins of 200/500 grams, diameter 155 cm, 6 ties, 2 doubles crosses- pre-treated yarn in skeins of 25/50/200/250 grams- pre-treated yarn in balls of 25/50 grams

For any further clarification of information, please contact our commercial offices: by phone +39 (0574) 542043, by fax +39 (0574) 643947 or by e-mail info@naturalfantasy.it

LEGAL NOTICE

All the contents of this website are covered by copyright. Any reproduction, even partial, for commercial purposes is permitted only upon prior written authorisation from Natural Fantasy® Srl. The statements included on this site regarding products, tests and legal regulations are intended as exemplary and concern only Italy. We reserve the right to modify the products and the characteristics and specifications of the same without any notice. Consequently the illustrations and texts on the website contain details which may not necessarily correspond to the current proposal.

This website has been created with the greatest possible precision. Despite this, we can assume no responsibility as regards mistakes or the correctness of the information contained.

We decline any responsibility whatsoever for any damage directly or indirectly caused by the use of this website.