

# TECHNICAL SHEET

## Art. TIBET MELANGE

### GENERAL DETAILS

<b>NAME OF YARN:</b>	TIBET MELANGE
<b>METRIC COUNT:</b>	2/28.000
<b>TEXTILE COUNT:</b>	36 x 2
<b>NUMBER OF PLY:</b>	2
<b>COMPOSITION:</b>	100% Cashmere
<b>PUNCHED DATA CODES:</b>	100%WS
<b>TYPE OF YARN:</b>	Linear classic
<b>SPINNING SYSTEM:</b>	Woollen
<b>CONVENTIONAL RATE APPLIED:</b>	17%
<b>AVERAGE REGAIN RATE APPLIED:</b>	3,8% ÷ 4,2%

### MATERIAL SPECIFICATIONS

<b>TYPE OF FIBRE:</b>	Cashmere	
<b>ANIMAL FROM WHICH IT IS HARVESTED:</b>	Goat	
<b>SCIENTIFIC CLASSIFICATION:</b>	<b>CLASS:</b>	<i>Mammalia</i>
	<b>ORDER:</b>	<i>Artiodactyla</i>
	<b>FAMILY:</b>	<i>Bovidae</i>
	<b>SUBFAMILY:</b>	<i>Caprinae</i>
	<b>GENUS:</b>	<i>Caprinae</i>
	<b>SPECIES:</b>	<i>Capra aegagrus hircus</i>

**ORIGIN OF THE FIBRE:** - Inner Mongolia (People's Republic of China)  
- Outer Mongolia (People's Republic of Mongolia)

**LENGTH OF THE FIBRE:** 38 mm

**AVERAGE FIBRE DIAMETER:** 14,5 ÷ 15,5 micron

**GRADE OF DEHAIRING** 0,01

## TYPE OF DYE

**MELANGE AND TOP DYED COLOURS:** Dyed on tops

## RECOMMENDED MACHINES

**FLAT KNITTING MACHINE:** 1 ply 12

**CUT COTTON MACHINE:** 1 ply 21 Gauges

## ADVICE FOR WORKING

- Re-paraffin the yarn at low speed immediately before putting it in the machine.
- Avoid particularly difficult stitches, and experiment the product thoroughly before utilising it for large quantities.
- NEVER use re-paraffined or re-reeled reels of yarn together with original reels.
- Check the cloth constantly during processing and in the case of evident defects suspend work and phone us to report the problem

## COMMERCIAL INFORMATION FOR ARTICLE TIBET MELANGE

**STOCK SERVICE MELANGE** 89 colours

**SHADE CARD REFERENCE** "CLASSIC CASHMERE"

**PRODUCTION MINIMUMS:** 3 Kg. for melange/chine colours  
60 Kg. for special colours

**EXTRA CHARGES** To view the extra charges for twisting, dyeing and shipment which we apply for small productions, refer to the commercial information menu.

**STANDARD PACK:** Cone of approx. 0,500 kg., each wrapped in a film of matt polythene to protect it from the light.

**For any further clarification of information, please contact our commercial offices: by phone +39 (0574) 542043,  
by fax +39 (0574) 643947 or by e-mail [info@naturalfantasy.it](mailto:info@naturalfantasy.it)**

---

#### **LEGAL NOTICE**

All the contents of this website are covered by copyright. Any reproduction even partial, for commercial purposes is permitted only upon prior written authorisation from Natural Fantasy® SpA. The statements included on this site regarding products, tests and legal regulations are intended as exemplary and concern only Italy. We reserve the right to modify the products and the characteristics and specifications of the same without any notice.

Consequently the illustrations and texts on the website contain details which may not necessarily correspond to the current proposal. This website has been created with the greatest possible precision. Despite this, we can assume no responsibility as regards mistakes or the correctness of the information contained.

We decline any responsibility whatsoever for any damage directly or indirectly caused by the use of this website.

---